

TEST REPORT

Number : SHAT07460136

Applicant : KASLEN TEXTILES
2140 E. 51st STREET
VERNON, CA 90058
Attn : JENNIFER NAGY

Date : Nov 04, 2022

Sample Description As Declared :

No. Of Sample : One
Fibre Content : 100% Polyester
Material : Sheer Woven Fabric
Finishing : -
End Uses : -
Colour : #Stone
Style No. : STATS
Order No./PO No. : -
Buyer's Name : -
Manufacturer's Name : -
Ref. : -

Applicant's Provided Care Instruction/Label : -

Date Sample Received : Nov 01, 2022

Date Testing Started : Nov 01, 2022

Conclusion:

The Submitted Sample Meets The Requirements Stated In National Fire Protection Association No. 701:2019
Method 1 Small Scale For Fire Tests Of Flame Resistant Textiles & Films.

Prepared And Checked By:
For Intertek Testing Services Ltd., Shanghai



Jane Wu
General Manager of Softlines

TEST REPORT

Number : SHAT07460136

Tests Conducted (As Requested By The Applicant)

- 1 Flammability Test (NFPA 701 - Standard Methods Of Fire Test For Flame Propagation Of Textiles And Films 2019 Edition, Test Method 1)

Test Results:						
Original State:						
Specimen	<u>Afterflame Time</u> (Seconds)	<u>Burning Time For Specimen That Falls To The Bottom Of The Test Chamber</u> (Seconds)	<u>The Formation Of Flaming Droplets</u> (Y/N)	<u>Weight Before Exposure</u> (Grams)	<u>Weight After Exposure</u> (Grams)	<u>Weight Loss</u> (%)
Test 1	0	0	N	12.5	10.0	20.0
Test 2	0	0	N	12.4	9.8	21.0
Test 3	0	0	N	12.5	9.9	20.8
Test 4	0	0	N	12.4	9.5	23.4
Test 5	0	0	N	12.4	10.3	16.9
Test 6	0	0	N	12.4	10.5	15.3
Test 7	0	0	N	12.5	9.7	22.4
Test 8	0	0	N	12.5	10.6	15.2
Test 9	0	0	N	12.5	9.2	26.4
Test 10	0	0	N	12.4	10.1	18.5
Average Burning Time For Specimen That Falls To The Bottom Of The Test Chamber: 0 Seconds						
Average Percent Weight Loss: 20.0						
Standard Deviation: 3.6%						
<u>Failure Criteria:</u>						
Average Burning Time For Specimen That Falls To The Bottom Of The Test Chamber: (Seconds)			Weight Loss (Percent)			
			Mean	Individual Specimen		
Exceeds 2.0			Exceeds 40%	Exceeds Mean + 3 Std.Dev		
Retest Provision: When The Percent Weight Loss Of Any Individual Specimen Exceeds The Mean Value Plus 3 Standard Deviations, The Test Shall Be Repeated On Another Sample Of 10 Specimens.						

Test Was Conducted Only In The Original State By The Client's Request

End of Report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

This report shall not be reproduced except in full, without written approval of the laboratory.

Intertek Testing Services Ltd., Shanghai

2/F, Building No.4, Shanghai Comalong Technology Service Park,
889 Yishan Road, Shanghai 200233, China
上海天祥质量技术服务有限公司

中国上海宜山路 889 号上海齐来科技服务园区 4 号楼 2 楼 邮编:200233
Tel: +86 21 5339 5999 Fax: +86 21 5426 2030 E-mail: textile.shanghai@intertek.com Website: Intertek.com
Attention is drawn to the terms and conditions printed overleaf