



Report Number: 84341 Date: 1-5-2016

For the Account Of:	Heritage Fabrics LLC 4400 Fortune Ave Concord, NC 28027 Etta - Ice 7P6-423				
Contact:	Concord, NC 28027 Woody Lowdermilk		⊏lla	- ICE 7F0-423	
Client's Identification:	HASHTAG				
TEST PERFORMED	NFPA 701 Standard N	Methods of Fire T	est for Flame Propa	agation of Textiles an	nd Films 2010 – Test #1
TEST RESULTS					
Specimen	Initial Mass	Final Mass	Mass Loss (%)	Flaming Drip	Afterflame
1	(g) 13.4	(g) 10.2	24%	(s) O	(s) O
2	13.4	10.5	22%	4	0
3	13.3	10.3	22%	Ö	Ö
4	13.4	9.9	26%	0	0
5	13.1	10.6	19%	0	0
6	13.0	10.1	22%	2	0
7	13.4	11.4	15%	6	0
8	13.3	10.1	24%	0	0
9	13.5	10.4	23%	0	0
10	13.5	10.5	22%	4	0
Average Approximate weight (oz./s	13.3 sq. yd): 6.5	10.4	22%	1.6	0.0
Product Configuration: ☐ Single Layer ☐ Multi Layer Conditioning: ☐ Oven at 220°F for minimum 30 minutes Intended End-use (if known & other than drapery): □ 70 ±2°F & 65 ±2%RH for minimum 24 hours					
Afterflame is required to be recorded; however, it is not factored into the Acceptance Criteria 1. Where fragments or residues of specimens that fall to the floor of the test chamber continue to burn for more than an average of 2 seconds per specimen for the sample of 10 specimens, the material shall be recorded as failing. (Flaming Drip) 2. Where the average weight loss of the 10 specimens in a sample is greater than 40 percent, the material shall be recorded as failing. 3. Individual specimens will be listed as a failure if it exceeds mean + 3 SD 4. Where the specimens do not demonstrate performance in accordance with either of the conditions indicated above, the material shall be recorded as passing this test and shall be designated as flame resistant. CONCLUSION Based on the above Results and Acceptance Criteria, the item tested: Complies Does Not Comply Testing of 10 additional specimens is required					

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature CR