

TEST REPORT

NUMBER : BOMT17043379

DATE : 19-Aug-2017

Mermaid-Gold 9H8-371
Mermaid-Charcoal 9H8-185
Mermaid-Rouge 9H8-713
Mermaid-Slate 9H8-800
Mermaid-Olive 9H8-541

TEST CONDUCTED (AS REQUESTED BY THE APPLICANT)

1. FLAMMABILITY TEST

- NFPA 701 - 1

	BURNING OF DRIPPINGS (Sec)	WEIGHT BEFORE EXPOSURE (Grams)	WEIGHT AFTER EXPOSURE (Grams)	%WEIGHT LOSS (%)
Test 1	2	19.43	16.83	13.38
Test 2	1	19.15	16.02	16.34
Test 3	1	19.09	16.27	14.77
Test 4	1	19.04	15.27	19.80
Test 5	2	19.10	16.80	12.04
Test 6	2	18.96	16.53	12.82
Test 7	2	18.82	15.92	15.41
Test 8	2	19.03	15.96	16.13
Test 9	1	18.98	16.18	14.75
Test 10	1	18.97	15.99	15.71
AVERAGE				15.12
STD.DEV				2.1838

Requirement:

2 Sec

Conclusion: PASS

1. Burning of Drippings:

Where fragments or residues of specimens that fall to the floor of test chamber continue to burn for more than an average 2 seconds per specimen for the sample of 10 specimens, the material shall be recorded as failing Test.

2. Average Percent weight:

Where the average weight loss of the 10 specimens in sample is greater than 40 percent, the material shall be recorded as failing Test.

The fabric submitted for testing Pass the flam resistance requirements when tested, as received, in accordance with the procedure outlined in the NFPA 701, Method 1.

END OF THE TEST REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Addressee in respect of this report and only accepts liability to the Addressee insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute.