



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

January 15, 2020

Ms. Jenna Stern
BELLE MAISON TEXTILES, INC.
89-50 127th Street
Richmond Hill, NY 11418

Windshire-Linen AH5-455
Windshire-Snow AH5-805
Windshire-Vanilla AH5-865

Reference: Laboratory Test Report
Lab Identification No. 39710
Invoice No. 70894

Dear Ms. Stern:

One (1) fabric sample, identified as **STYLE: JUSTIN; CONTENT: 100% POLYESTER**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2019 Edition, (Test 1)". The results are as follows:

Test Results

<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	25.91
2	0.0	27.11
3	0.0	25.95
4	3.0	30.21
5	0.0	25.31
6	0.0	24.65
7	0.0	28.17
8	4.0	21.32
9	4.0	31.38
<u>10</u>	<u>0.0</u>	<u>24.09</u>
AVG	1.1	26.41

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

