



Test Report

No. HZ1111462/TX

Date: Apr 7, 2011

Page 1 of 4

The following sample(s) was/were submitted and identified by the client as:

Sample Description : Two samples of PVC coated screen- : 70% PVC,30% polyester in (A)
white (B) beige for windows shading system

Style No. : T10-3001; A5-4048

Manufacturer :


Test Performed : Selected test(s) as requested by applicant

Sample Receiving Date : MAR. 29, 2011

Test Period Date : MAR. 29, 2011- APR. 07, 2011

Test Result(s) : For further details, please refer to the following page(s).

Signed for and on behalf of
SGS-CSTC Ltd.


Alex Wang (Account Executive)

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, compensation and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its inspection only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated, the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

SGS Standards Technical Services Co., Ltd.
Hangzhou

5F, 5F-A, Building A, H-Tech Industrial Park No. 1120 Bin'an Road, Binjiang District, Hangzhou, China 310052
中国·杭州·萧山区（滨江）开发区滨安路11804号华业科技园4号楼5、6楼 邮编：310052

HZTX 837311
I (86-571)86791109 I (86-571)87688901 www.cn.sgs.com
I (86-571)86791169 I (86-571)87688901 e sgs.china@sgs.com

Member of the SGS Group (SGS SA)

Test Report

No. HZ1111462/TX

Date: Apr 7, 2011

Page 2 of 4

Test Result

I. Test Conducted*

This test was conducted in accordance with test method 1 of NFPA 701:2010 Standard Methods of Fire Tests for Flame Propagation of Textiles and Films.

II. Details of tested sample

Materials	Fabric
Color	1. Sample A: White; 2. Sample B: Beige
Area Density	1. Sample A: About 400g/m ² ; 2. Sample B: About 525g/m ²
Products configuration	Single layer
Size of sample *	150mm × 400mm 10pcs

* With the length parallel to the lengthwise direction of the material

III. Conditioning

Prior to testing, the sample was conditioned,

at least 30 minutes at 105°C±3°C (220°F±5°F)

IV. Test results

1) Sample A

Specimen No	Mass of specimen Before test (g)	Mass of specimen After test (g)	Mass loss (Percent)	After flame time (s)	Burning time on floor (s)
1	24.00	21.64	9.8	0.0	0.0
2	23.86	21.62	9.4	2.8	0.0
3	23.91	22.37	6.4	0.0	0.0
4	24.32	21.98	9.6	0.0	0.0
5	24.16	22.34	7.5	2.4	0.0
6	23.76	22.54	5.1	0.0	0.0
7	23.85	22.09	7.4	0.0	0.0
8	24.06	22.81	5.2	1.8	0.0
9	23.96	22.64	5.5	0.0	0.0
10	24.11	22.34	7.3	2.6	0.0
Mean	24.00	22.24	7.3	1.1	0.0

SD = 1.8

3SD = 5.4

Mean + 3SD = 12.7 SD - Standards deviation

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its issuance and only within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated, the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.



5F&6F Building, Hangzhou Industrial Park, No. 1100 Binshan Road, Binjiang District, Hangzhou, China 310052

t (86-571)86791199

f (86-571)87688901

www.cn.sgs.com

中国·杭州·高新(滨江)开发区滨安路1100号华业科技园4号楼5、6楼 邮编: 310052

t (86-571)86791199

f (86-571)87688901

e sgs.china@sgs.com

HZTX 837310

Member of the SGS Group (SGS SA)

Test Report

No. HZ1111462/TX

Date: Apr 7, 2011

Page 3 of 4

Observations:

Vigorousness of burning	No
Material molten dripping	No
Odor smoke	Yes

2) Sample B

Specimen No.	Mass of specimen Before test (g)	Mass of specimen After test (g)	Mass loss (Percent)	After flame time (s)	Burning time on floor (s)
1	31.50	29.61	6.0	3.6	0.0
2	31.08	28.84	7.2	0.0	0.0
3	31.92	29.11	8.8	0.0	0.0
4	32.13	29.85	7.1	2.9	0.0
5	31.82	28.79	9.5	4.1	0.0
6	32.26	29.76	7.7	0.0	0.0
7	30.93	29.46	4.8	0.0	0.0
8	32.07	28.78	10.3	2.6	0.0
9	30.84	28.86	6.4	5.2	0.0
10	30.64	29.04	5.2	0.0	0.0
Mean	31.52	29.21	7.3	1.8	0.0

SD = 1.8

3SD = 5.4

Mean + 3SD = 12.7 SD - Standards deviation

Observations:

Vigorousness of burning	No
Material molten dripping	No
Odor smoke	Yes

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, jurisdiction and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its inspection only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Please be advised that the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.



SGS SCS (Shanghai) Textile Laboratory

5F&6F Building Huayao Industrial Park, No. 1180 Binbin Road, Binjiang District, Hangzhou, China 310052

Tel: (86-571) 88791199

Fax: (86-571) 87668901

www.cn.sgs.com
e: sgs.china@sgs.com

HZTX 837309

Member of the SGS Group (SGS SCS)

Test Report

No. HZ1111462/TX

Date: Apr 7, 2011


Page 4 of 4

Criteria for test method 1 (Chapter 10):

1. Fragments or residues of specimens that fall to the floor of the test chamber shall not continue to burn for more than an average of 2 seconds per specimen for the sample of 10 specimen.
2. The average weight loss of the 10 specimen in a sample shall be 40 percent or less.
3. No individual specimen's percent mass loss shall deviate more than 3 standard deviations from the mean for the 10 specimens.
4. When a retest is required, no individual specimen's percent mass loss in the second set of specimens shall deviate from the mean value by more than 3 standard deviations calculated for the second set.
5. When a sample does not demonstrate passing performance in accordance with all of the conditions indicated above, the material shall be recorded as having failed Test Method 1.

Conclusion: The tested sample "As received" meets the requirements of Test Method 1 of NFPA 701:2010

Photo Appendix:



* This test was carried out by SGS A.J. Laboratory

End of Report

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and for electronic formal documents subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, jurisdiction and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its issuance and is only valid within the limits of Client's Instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated, the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

SGS Standards Technical Services Co., Ltd.
Hangzhou China - Test Laboratory

SGS A.J. Testing Service Industrial Park No. 1190, Bin'an Road, Binjiang District, Hangzhou, China 310052
中国·杭州·滨江区 滨安路1190号 华业科技园4号楼5、6楼 邮编: 310052

1 (86-571)86791199
1 (86-571)86791199

1 (86-571)87688901
1 (86-571)87688901

www.cn.sgs.com
sgs.china@sgs.com

HZTX 837308

Member of the SGS Group (SGS SA)